

Free Email

mail.com

Delphion Intellectual Property Network

[IPN Home](#) | [Search](#) | [Order](#) | [Shopping Cart](#) | [Login](#) | [Site Map](#) | [Help](#)



JP2241014A2: SOLID ELECTROLYTIC CAPACITOR

[View Images \(1 pages\)](#) | [View INPADOC only](#)

Country: **JP Japan**

Kind:

Inventor(s): **KURIHARA KANAME
SHIMIZU HIDEO
SHIRAI KOZO
KURIHARA HIROYUKI**

Applicant(s): **ELNA CO LTD**
[News, Profiles, Stocks and More about this company](#)

Issued/Filed Dates: **Sept. 25, 1990 / March 15, 1989**

Application Number: **JP1989000062923**

IPC Class: **H01G 9/02;**

Abstract: **Purpose:** To obtain a device of high performance and reliability in which new organic semiconductor having small resistivity and thermal stability is used as solid-state electrolyte, by using specified bis(amidinohydrazone) dielectric TCNQ salt as the solid electrolyte. **Constitution:** As electrolyte, bis(amidinohydrazone) dielectric 7,7,8,8-tetracyanoquimodimethane salt shown by a formula 1 is used. R in the formula represents diacetyl, p-quinon or terephthalaldehyd. For example, diacetyl-bis(amidinohydrazone) TCNQ salt is dissolved in acetonitrile, and saturated solution is obtained; after a capacitance element is dipped in the solution, vacuum drying is performed at 50-60°C, thereby dispersing acetonitrile as the solvent; the above operation is repeated three times. An aluminum foil whose surface is etched at about ten times is used as the electrode of a capacitor element, and further the surface is subjected to formation treatment, thereby forming an oxide film.

COPYRIGHT: (C)1990,JPO&Japio

Other Abstract Info: **DERABS C90-332721 DERC90-332721**

Foreign References: **(No patents reference this one)**

Powered by **DB2**
and **Net Data**

[Nominate this invention for the Gallery...](#)

Alternative Searches

[Patent Number](#)

[Boolean Text](#)

[Advanced Text](#)

Browse

[U.S. Class by title](#)

[U.S. Class by number](#)

TDB
[IBM Technical Disclosure Bulletin](#)